



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D21G 3/00 // 3/02, 3/04, B41F 15/44	A1	(11) International Publication Number: WO 00/15904 (43) International Publication Date: 23 March 2000 (23.03.00)
(21) International Application Number: PCT/FI99/00729 (22) International Filing Date: 9 September 1999 (09.09.99) (30) Priority Data: 981945 10 September 1998 (10.09.98) FI (71) Applicant (for all designated States except US): VALMET CORPORATION [FI/FI]; Fabianinkatu 9 A, FIN-00130 Helsinki (FI). (72) Inventors; and (75) Inventors/Applicants (for US only): KIRJAVA, Jouni [FI/FI]; Jussilantie 18, FIN-36110 Ruutana (FI). RATA, Ilkka [FI/FI]; Vitsiälänkatu 4, FIN-40520 Jyväskylä (FI). VAINIO, Tommi [FI/FI]; Lummetie 13 B 15, FIN-01300 Vantaa (FI). (74) Agent: FORSSÉN & SALOMAA OY; Yrjönkatu 30, FIN-00100 Helsinki (FI).		(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: DOCTOR BLADE (57) Abstract A doctor blade for use in cleaning of a roll in a paper machine. The doctor blade comprises a thermosetting plastic polymer material, whose glass transition temperature T _g is 20...30 °C higher than its operating temperature, and the resistance of the material to impacts is high.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Doctor blade

5

The invention concerns a doctor blade for a paper machine as defined in the preamble of claim 1.

10 Faces of rolls in a paper/board machine tend to be coated with impurities derived from the process and with material from a doctor blade. Doctor blades are used in order to remove these materials from roll faces. With increasing running speeds of paper machines, it has proved to be a problem that the materials used in doctor blades do not endure these speeds of paper machines higher than 1400 metres per minute but start melting and are abraded rapidly, in which case they no longer
15 operate in cleaning of the roll face.

Thus, an object of the present invention is to provide such a material for a doctor blade as endures higher running speeds of a paper machine and, thus, high operating temperatures.

20

An object of the present invention is to provide a doctor blade which, besides a high operating temperature, also possesses good mechanical strength and rigidity.

From the prior art, many doctor blades made of different materials are known,
25 including composite structures, and with respect to the prior art reference can be made, for example, to *US Patent 4,549,933*, published *DE Patent Application 4137970*, *FI Patent 101,637*, and to the *Japanese publications 05-214696*, *05-321189*, and *05-132891*.

30 In the *US Patent 4,549,933*, a doctor blade for a paper machine is described, which blade consists of a number of alternating layers of fibre and carbon fibre so that a fibre layer can consist of cotton, paper, fibreglass, or equivalent.

On the other hand, in the published *DE Patent Application 4137970*, the use of fibre-reinforced plastic, e.g., in a doctor blade is suggested, in which blade, the fibre-reinforced plastic contains 60...90 per cent by weight of polyamide-6 or of polyamide-66 and 10...40 per cent by weight of reinforcement fibres. A polyamide, which is a thermoplastic resin, is used in order to increase the thermal conductivity.

In the *FI Patent 101,637*, a caring doctor blade is described, which comprises a number of fibre layers as a laminate construction and whose construction comprises at least one layer of carbon fibre or at least one layer that contains a substantial proportion of carbon fibre and that contains grinding particles in direct vicinity of the carbon fibres and in which the carbon fibres are oriented substantially obliquely in relation to the direction of the longitudinal axis of the blade, favourably in the cross direction of the blade.

In the *JP publication 05-214696*, a doctor blade is described, in which polyethylene of very high molecular weight or fibre-reinforced polyethylene of very high molecular weight has been employed, which polyethylene is a thermoplastic resin.

In the *JP publication 05-321189*, a doctor blade is described which is made of a thermoplastic fibre composite material which contains 30...80 per cent by weight of polyphenylene sulphide, which is a thermoplastic resin, and 20...70 per cent by weight of either glass fibres, aramide fibres, or graphite fibres.

In the *JP publication 05-132891*, a doctor blade is described which consists of a material that contains fibreglass, in which material the fibres made of filaments have been immobilized in a resin parent material, such as epoxy resin.

As comes out from the above prior art, a number of different thermoplastic resin materials have been suggested for the matrix material. In spite of their possible good properties of resistance to heat, thermoplastic resins have not achieved commercial importance as doctor materials because of their high cost and because of their difficult workability. A thermosetting plastic from which high resistance to heat in

operation is expected also requires a considerably high melting-processing temperature. In practice, in commercial products, almost exclusively epoxy resins have been used.

5 A problem of doctor blades that comprise an epoxy matrix is their rapid wear and the resulting shorter service life. With increasing running speeds of machines the problem has become even worse. A higher speed increases the friction heat between the revolving roll and the doctor blade. The epoxy starts becoming soft and melts. The phenomenon of softening is increased by the wet conditions, for epoxy has a
10 tendency of a certain degree to absorb water. The softening and the melting have the effect that the roll face is coated with the matrix material. This again causes changes in the properties of adhesion, separation and surface energy in the roll face, which properties are ever more critical in view of the runnability of the machine.

15 A second serious drawback of epoxy is its poor suitability for pultrusion and for similar methods by whose means continuous manufacture of doctor blades would be possible.

In view of achieving the objectives stated above and those that will come out later,
20 the doctor blade in accordance with the invention is mainly characterized in what is stated in claim 1.

The problems that have come out in the prior art have been overcome in the present invention by means of new matrix materials. These materials are thermosetting
25 plastic materials of which it is characteristic that their glass transition temperature T_g is sufficiently, at least about 20...30 °C, higher than the temperature to which the matrix is subjected in a situation of operation, and which materials have good impact strength. As the matrix does not come close to its T_g temperature during operation, its wear as a result of softening/melting is slower. Also, in such a case, the wear
30 takes place in a controlled way without breaking of the tip of the blade. Controlled wear is important in order that the blade should remain sharp through its whole service life. Owing to high impact strength, the blade tip is not broken equally easily

if some material adhering to the roll face passes under the blade in a running situation.

Owing to their nature of thermosetting plastic, the materials in accordance with the present invention are suitable for being processed by means of all methods that are used with thermosetting plastics, including pultrusion, and they do not require considerable elevated temperatures, as the thermoplastic resin materials do. In the manufacture of oblong pieces, suitability for pultrusion is a highly desirable feature, because it permits continuous manufacture, in which case the overall economy of the manufacture is better and the product is of uniform quality.

In accordance with a preferred embodiment of the invention, the doctor blades are composite structures and consist of a polymer matrix and of reinforcements and of possible filler materials. The reinforcements can be conventional fibre reinforcements, such as glass, carbon or aramide fibres or structures woven out of said materials or mixtures of said fibre reinforcements. For example, a multi-layer structure can be made of such a mixture, in which structure fibreglass and carbon fibre reinforcements and the alignment of said reinforcement fibres vary/alternate in different layers.

In accordance with an embodiment of the invention, as the matrix material in this composite structure a new polymer material of the type of thermosetting plastic is used. This material consists of a polyester-based polyol dissolved in styrene and of polyisocyanate. In the first stage of the reaction, when the polyol component reacts with isocyanate, in a what is called chain extension reaction, urethane bonds are formed. In the second stage of the reaction, the double bonds in the polyester polyol react with the styrene as radical polymerization and cross-link a network structure typical of thermoplastic resins in the material.

The polymer that is formed is vinylesterurethane, which has a what is called hybrid structure in which there is both a urethane bond known from polyurethanes and a bond typical of vinylesters. The first and the second stage of the reaction take place

typically at the same time. There are several different accelerator and initiator systems by whose means the speeds of the reactions can be controlled. By their means and by means of selection of the polyester polyol it is possible to regulate the properties of the material of the doctor blade so that they become as desired in view
5 of the purpose of use and of the processing method.

Besides the good mechanical properties of vinylesterurethane (strength, module and toughness values equal or exceed typical values of polyester/epoxy materials with high toleration of temperature) said material has an excellent toleration of tempera-
10 ture, the HDT temperature is up to 220 °C. Thus, it is suitable for a material for doctor blades in particular in modern high-speed paper machines, in which the surface temperatures of doctor blades become quite high.

The good mechanical properties of vinylesterurethane and its excellent toleration of
15 chemicals are retained at elevated temperatures, and it tolerates thermal ageing well.


The raw-materials of vinylesterurethane are in solution form, and it can be processed by means of methods typical of thermosetting plastics. In the manufacture of doctor blades in accordance with the present invention, preferably pultrusion is used.
20 Further possible methods are, for example, manufacture by means of prepregs (setting and autoclave treatment), by means of resin injection (RTM), or by means of reactive injection moulding.

In pultrusion, the speed of manufacture with vinylesterurethane is up to four times
25 higher than with vinylesters, which lowers the cost of manufacture. The adhesion of vinylesterurethanes to different fillers is good, and, for example, ceramic and metallic fillers or cut-off-fibre reinforcements can be employed in addition to woven fibre reinforcements.

30 In accordance with an embodiment of the invention, the matrix of a composite structure is a thermosetting plastic named polyether amide (Polyether Amide Resin

= PEAR), which has been obtained from a reaction between bisoxazoline and a phenolic compound. The structure of this polymer is illustrated in a formula below describing structural units of polyether amide and structure of cross-linked polymer.

5



15

20

The polymer illustrated in the formula has the following good properties expressly as a material for a doctor blade:

25

- excellent thermal stability in constant operation up to 180 °C.
- good adhesion to glass fibres and carbon fibres and to metals (aluminum, steel) and to ceramics because of its chemical structure
- good toughness (5-fold G_{1c} value as compared with epoxy)
- 30 — glass transition temperatures 225...295 °C, depending on the hardening cycle and on the material modification

SUBSTITUTE SHEET (RULE 26)

- the modulus of elasticity of pure non-reinforced polyether amide in the category of thermosetting plastics is very high (about 5100 MPa)
 - does not contain volatile components
 - low coefficient of thermal expansion ($42 \times 10^{-6}/^{\circ}\text{C}$) as compared with other
- 5 polymers.

Polyether amide is available as a solution and as a "hot melt" version. Polyether amide in solution form is, as a rule, used for the preparation of preregs, in which case fibre reinforcements are impregnated with a solution that contains a polymer

10 and a suitable solvent. The hot melt polymer is directly usable, for example, in a RTM method or in pultrusion, provided that the components are heated (about 160 °C) in order to lower the viscosity to a suitable level.

In the manufacture of the doctor blades in accordance with the present invention, the

15 following techniques can be applied, which techniques are also suitable for other thermosetting plastics:

- manufacture by means of preregs (setting and autoclave treatment)
- pultrusion
- 20 — compression moulding
- RTM (resin transfer moulding)

From the point of view of the manufacture, with polyether amide the following advantages are obtained:

- 25
- very low exothermic generation of heat during hardening reaction (5 times lower than with epoxies and 10 times lower than with bismaleimides) → even thick parts are possible
 - low hardening shrinkage ($< 0.8 \%$; with epoxy about 3 %)
 - 30 — autoclave treatments 180 °C
 - after-hardening in an oven 180...230 °C

Since polyether amide has good adhesion, among other things, to ceramics and to metals, into the matrix, if necessary, e.g., various ceramic or metallic filler particles can be mixed without considerable deterioration of the mechanical properties of the material.

5

It has been noticed that doctor blades in accordance with the present invention have a remarkably improved resistance to wear and a prolonged service life as compared with blades that contain an epoxy matrix.

10 Above, the invention has been described with reference to some preferred exemplifying embodiments of same only, and many modifications and variations are possible within the scope of the inventive idea defined in the following patent claims.

Claims

1. A doctor blade for use in cleaning of a roll in a paper machine, which blade comprises a thermosetting plastic polymer material, **characterized** in that the glass transition temperature T_g of the polymer material is 20...30 °C higher than its operating temperature and that the resistance of the material to impacts is high.
2. A doctor blade as claimed in claim 1, **characterized** in that the polymer material is vinylesterurethane.
3. A doctor blade as claimed in claim 1, **characterized** in that the polymer material is polyether amide.
4. A doctor blade as claimed in claim 1, **characterized** in that the doctor blade contains reinforcement fibres and/or filler materials.
5. A doctor blade as claimed in claim 4, **characterized** in that the blade has been manufactured by means of pultrusion.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 99/00729

A. CLASSIFICATION OF SUBJECT MATTER

IPC7: D21G 3/00 // D21G 3/02, D21G 3/04, B41F 15/44
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: D21G, B41F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0448043 A1 (PHILIPS PETROLEUM COMPANY), 25 Sept 1991 (25.09.91), page 2, line 3 - line 30; page 3, line 3 - line 5, abstract	1,4
A	page 2, line 3 - line 30; page 3, line 3 - line 5, abstract	2,3
	--	
X	EP 0454404 A1 (ALBANY INTERNATIONAL CORP.), 30 October 1991 (30.10.91), column 5, line 27 - line 32, abstract	1,4
	--	
X	WO 9904091 A1 (VALMET CORPORATION), 28 January 1999 (28.01.99), page 2, line 31 - page 3, line 9, claims 1,3, abstract	1,3,4
	--	

☐ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document but published on or after the international filing date	"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search	Date of mailing of the international search report
22 December 1999	04 -01- 2000
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86	Authorized officer Mattias Arvidsson/ELY Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

02/12/99

International application No.

PCT/FI 99/00729

Patent document cited in search report			Publication date	Patent family member(s)		Publication date
EP	0448043	A1	25/09/91	CA	2031940 A	21/09/91
				JP	4222866 A	12/08/92
				US	5017643 A	21/05/91

EP	0454404	A1	30/10/91	AU	632661 B	07/01/93
				AU	7026591 A	13/02/92
				CA	2039301 A	24/10/91
				DK	73591 A	24/10/91
				EP	0454403 A	30/10/91
				FI	910481 A	24/10/91
				JP	4228695 A	18/08/92
				NO	911578 A	24/10/91
				NZ	236947 A	26/03/93
				US	5110415 A	05/05/92

WO	9904091	A1	28/01/99	AU	7921898 A	10/02/99
				FI	3131 U	04/11/97
				FI	970331 V	15/07/97
